



Ameron International Corporation
PROTECTIVE LININGS DIVISION
201 North Berry Street
P.O. Box 1629
Brea, CA 92822-1629

June 20, 2012

Fax: 563-263-3014

Fabricators Plus
3206 Hershey Ave.
Muscatine, IA 52761

Phone: 714-256-7755
Fax: 714-256-7750

www.amerondjock.com

ISO 9001:2008 Registered Firm
Certificate No. A2540US

Project Name: Large Anodizing Tank Line

Gentlemen:

In response to your **June 13, 2012** submission of test welds taken from a qualification welding test administered by you or under your direction in accordance with:



Project, Specification Section _____
The physical test requirements of Section 311-1.2.2 of the Standard Specifications for Public Works (the "Greenbook") is published by BNI, Inc. in Anaheim, CA and ASTM D412.

This test was witnessed by **John Pico, Ameron Field Service Representative.**

As a requirement the successful PSI test results must be 2000 or better. The qualification welding test results for each welder are valid for a period of two years.

Ameron has performed the required laboratory testing at the Quality Control Laboratory of Ameron Protective Lining Products located at Brea, California. The submitted test sample results are as follows:

Average Tensile Strength Of Sample/ PSI
2200
2268
2269
2290
2361
2373

Please remember that at any time you, or your representatives, feel it is appropriate, or the Engineer determines re-qualification is necessary, you can initiate re-qualification testing of any welder and submit the test weld to Ameron for testing (see Section 311-1.2.2 of the Standard Specifications for Public Works.)

Best regards,

John Pico
Field Service Representative

STATE OF CALIFORNIA, COUNTY OF ORANGE
Witnessed on the 20th day of June 2012